
gummi-plast

GmbH & Co.KG

Gernsheim



**Profiles of rubber, sponge rubber,
silicone, foam silicone**

D-64579 Gernsheim - Germany

Otto-Hahn-Straße 12

Telefon +49 (0) 62 58 / 932250

Telefax +49 (0) 62 58 / 4997

e-mail: info@gummi-plast.de

internet: <http://www.gummi-plast.de>

<http://www.gummi-plast.com>

complete overview of technical information

list of contents

	side
sponge rubber in EPDM	3
sponge rubber in CR (Neoprene).....	4
sponge rubber in NBR (Perbunan)	5
sponge rubber in FPM/FKM (VITON®).....	6
foam silicone quality SPS.....	7
foam silicone quality SPS / FDA-conform.....	8
foam silicone quality SPS / HT.....	9
solid rubber in EPDM.....	10
comparison between NAAM and compound gummi-plast.....	11
solid rubber in CR (Neoprene)	12
solid rubber in NBR (Perbunan).....	13
solid rubber in FPM/FKM (VITON®)	14
solid rubber in NR (Nature Rubber).....	15
silicone rubber	16
PVC edge protecting profiles	17
self-adhesive tape for sponge rubber and solid rubber	18
self-adhesive tape <i>sk normal</i> for foam silicone and silicone.....	19
self-adhesive tape <i>sk super</i> for foam silicone and silicone.....	20
our factory standard for sponge rubber and solid rubber.....	21

important:

Functioning and endurance lifetime of sealing materials are depending especially on installation conditions, on which we have no effect as the producer. That's why we can guarantee only a flawless quality of our material. Our technical service is bases on experiences, the values are intended only as a source of information and are given without of guarantee and do not constitute a warranty. Any technical modifications are reserved by us.

VITON® = Entered registered trade mark of the company DuPont

technical information

sponge rubber in EPDM

elastomer: ETHYLENE-PROPYLENE-DIENE TERPOLYMERS (EPDM)
(no blend-quality)

special characteristics: continuous extruded and vulcanized

no adhesive-connection

100% cell-closed, all around closed skin even at cuts -
there is no water absorption

colour: black
(according to available request other colours)

density: a) ca. 0,5 g/cm³
b) ca. 0,6 – 0,8 g/cm³

dimensional tolerance: according to DIN ISO 3302-1 E3

resistance

temperature: from –35°C till +110°C

ozone, weathering, UV-light: black: very good to excellent
grey: limited – in relationship of outlet

oil and grease: vegetable very good
animal limited
mineral moderate

acid, alkaline, ketone, alcohol: excellent

lacquer: inert – only by peroxide vulcanisation
– not by sulphur vulcanisation

important:

Our technical service is based on experiences, the values are intended only as a source of information and are given without guarantee and do not constitute a warranty. Users should independently determine prior to use the suitability of this material for their purposes.

technical information

sponge rubber in CR (Neoprene)

elastomer:	POLYCHLOROPRENE (CR) (no blend-quality)
special characteristics:	continuous extruded and vulcanized no adhesive-connection 100% cell-closed, all around closed skin even at cuts - there is no water absorption
colour:	black
density:	ca. 0,4 – 0,6 g/cm ³
dimensional tolerance:	according to DIN ISO 3302-1 E3

resistance

temperature:	from –35°C to +110°C
ozone and weathering:	very good
oil and grease:	limited resistant
acid and alkaline:	very good

important:

Our technical service is based on experiences, the values are intended only as a source of information and are given without guarantee and do not constitute a warranty. Users should independently determine prior to use the suitability of this material for their purposes.

technical information

sponge rubber in NBR (Perbunan)

elastomer:	ACRYLONITRIL-BUTADIENE-COPOLYMER (NBR)
special characteristics:	continuous extruded and vulcanized no adhesive-connection 100% cell-closed, all around closed skin even at cuts - there is no water absorption
colour:	grey or black (according to available request other colours)
density:	ca. 0,35 g/cm ³
dimensional tolerance:	according to DIN ISO 3302-1 E3
compression set:	at 50% deformation after 22 h with 23°C = after 24 h discharge ≤ 25%.

Information on compression set is a nominal value, as the compression set is dependent on the geometry of the test specimen. The test was made on a cross section profile 20 x 20 mm..

resistance

temperature:	from -30°C till +80°C
fire:	not resistant
ozone, weathering, UV-light:	moderate
stiffening in cold:	good
cold brittleness:	good
aliphatic hydrocarbon:	good
aromatic hydrocarbon:	not resistant
ketone:	not resistant
oil and grease:	vegetable very good animal very good mineral very good
acid and alkaline:	limited till not resistant
water:	moderate
dielectric strength:	moderate

important:

Our technical service is based on experiences, the values are intended only as a source of information and are given without guarantee and do not constitute a warranty. Users should independently determine prior to use the suitability of this material for their purposes.

technical information

sponge rubber in FPM/FMQ (VITON®)

elastomer:	FLUOR RUBBER (FPM/FMQ)
special characteristics:	continuous extruded and vulcanized no adhesive-connection 100% cell-closed, all around closed skin even at cuts - there is no water absorption
colour:	black
density:	ca. 0,95 g/cm ³
dimensional tolerance:	according to DIN ISO 3302-1 E3

resistance

temperature:	from -20°C till +200°C, short-term +250 °C
ozone, weathering, UV-light:	very good
fire characteristic:	hard inflammable, self-extinguishing
chemicals:	excellent
hydrochloric-/sulphuric acid (50%):	very good
nitric acid (60%):	very good
hydrocarbon:	very good
oil and lubricant:	very good

important:

Our technical service is based on experiences, the values are intended only as a source of information and are given without guarantee and do not constitute a warranty. Users should independently determine prior to use the suitability of this material for their purposes.

VITON® = Entered registered trade mark of the company DuPont

technical information

foam silicone quality SPS

elastomer:	METHYLVINYLPOLYSILOXAN (VMQ)
special characteristics:	continuous extruded and vulcanized 100% cell-closed, all around closed skin water and organic-productions refused physiological clean and bacteriological indifferent contains no poisonous material not corrosive – not adhering
colour:	white (according to available request other colours)
density:	ca. 0,25 – 0,55 g/cm ³
dimensional tolerance:	according to DIN ISO 3302-1 E3 or ±10%

resistance

temperature:	from –60°C till ca.+220°C
weathering, age limit, ozone:	excellent
tropical-climate, ultraviolet rays:	excellent
radioactive- and x-rays:	very good
aliphatic motor- and gear oil:	general good
heat conductivity:	0,18 – 0,23 Kcal. x s ⁻¹ °C ⁻¹
specific heat:	0,3 cal. x gr ⁻¹ °C ⁻¹
fire characteristic:	normal inflammable and not dropping fire class DIN 4102, section 1, B2

Physical-mechanical values are depending on the cross-section of the profile. The quality performed the instructions of the American Material Specification AMS 3195.

important:

Our technical service is based on experiences, the values are intended only as a source of information and are given without guarantee and do not constitute a warranty. Users should independently determine prior to use the suitability of this material for their purposes.

technical information

foam silicone quality SPS / FDA conform

elastomer:	METHYLVINYLPOLYSILOXAN (VMQ)
special characteristics:	continuous extruded and vulcanized 100% cell-closed, all around closed skin water and organic-productions refused physiological clean and bacteriological indifferent contains no poisonous material not corrosive – not adhering
colour:	nature
density:	0,40 g/cm ³
shore:	15 ±5
tensile strength:	1,5 MPA
elongation:	300%
resistance to tearing:	5 kN
compression set:	after 22 hours with 100°C: < 50% (crushing 25%) (ASTM D 395-methode B)
dimensional tolerance:	according to DIN ISO 3302-1 E3 or ±10%
resistance	
temperature:	+200°C
FDA conform:	yes

important:

Our technical service is based on experiences, the values are intended only as a source of information and are given without guarantee and do not constitute a warranty. Users should independently determine prior to use the suitability of this material for their purposes.

technical information

foam silicone quality SPS / HT

elastomer:	METHYLVINYLPOLYSILOXAN (VMQ)
special characteristics:	continuous extruded and vulcanized 100% cell-closed, all around closed skin water and organic-productions refused physiological clean and bacteriological indifferent contains no poisonous material not corrosive – not adhering
colour:	white
density:	ca. 0,25 g/cm ³
dimensional tolerance:	according to DIN ISO 3302-1 E3 or ±10%
resistance	
temperature:	from –60°C till ca.+220°C; for a short time till +300°C
weathering, age limit, ozone:	excellent
tropical-climate, ultraviolet rays:	excellent
radioactive- and x-rays:	very good
aliphatic motor- and gear oil:	general good
heat conductivity:	0,18 – 0,23 Kcal. x s ⁻¹ °C ⁻¹
specific heat:	0,3 cal. x gr ⁻¹ °C ⁻¹
fire characteristic:	normal inflammable and not dropping fire class DIN 4102, section 1, B2

Physical-mechanical values are depending on the cross-section of the profile. The quality performed the instructions of the American Material Specification AMS 3195, AMS 3196 and BMS 1-60

important:

Our technical service is based on experiences, the values are intended only as a source of information and are given without guarantee and do not constitute a warranty. Users should independently determine prior to use the suitability of this material for their purposes.

technical information

solid rubber in EPDM

elastomer:	ETHYLENE-PROPYLENE-DIENE-TERPOLYMERS (EPDM) (no blend-quality)
special characteristics:	homogenous continuous extruded and vulcanized no adhesive-connection
colour:	black (according to available request other colours)
density:	ca. 1,15 – 1,25 g/cm ³
shore:	40 – 55 – 65 – 75 – 85 ±5
dimensional tolerance:	according to DIN ISO 3302-1 E2

resistance

temperature:	from –35°C till +120°C
ozone, weathering, UV-light:	black: very good to excellent grey: limited – in relationship of outlet
oil and grease:	vegetable very good animal limited mineral moderate
acid, base, ketone, alcohol:	excellent
lacquer:	inert – only by peroxide vulcanisation – not by sulphur vulcanisation

important:

Our technical service is based on experiences, the values are intended only as a source of information and are given without guarantee and do not constitute a warranty. Users should independently determine prior to use the suitability of this material for their purposes.

**comparison between the instructions
NAAM – DIN 7863
and compound gummi-plast – EPDM
hardness 60/65 shore**

A: 70 hours +100 °C

B: 7 days +100 °C

C: 14 days +100 °C

	NAAM-Stand SG – 1 – 70	gummi-plast EPDM 60 Sh			DIN 7863
hardness shore A	60 / 65 ±5	60 / 65 ±5			60 / 65 ±5
tensile strength kg/cm²	mind. 127	120			mind. 85
elongation at break %	mind. 250	330			mind. 200
compression set %	mind. 25	24,5			max. 35
age limit	(70 h +100 °C) 70 h +100 °C	(70 h +100 °C) A B C			(22 h +100 °C) 7 days +100 °C
Δ hardness (grade)	max. +10	+0	+1	+4	max. +15 –5
Δ tensile strength	max. –15	+3	+5	+7	max. –25
Δ elongation %	max. –40	+1	+3	+3	max. –50
examination at lower temperature (ASTMD – 746)	-40 °C	acc. the ASTM – 746 examination satisfactory			---
examination at lower temperature (DIN 53505 7 days –10 °C)	---	no information at order			+12 Sh
ozone resistance	no split (1 ppm. 20% expansibility 100 h +40 °C)	no split (1 ppm. 20% expansibility 100 h +40 °C)			no split (50 ppm. 20% expansibility 100 h +40 °C)

technical information

solid rubber in CR (Neoprene)

elastomer:	POLYCHLOROPRENE (CR)
special characteristics:	homogenous continuous extruded and vulcanized no adhesive-connection
colour:	black (according to available request other colours)
density:	ca. 1,35 – 1,45 g/cm ³
shore:	50 – 60 – 70 – 80 ±5
elongation at break:	300 – 350%
compression set:	27 – 28%
dimensional tolerance:	according to DIN ISO 3302-1 E2

resistance

temperature:	from –35°C till +110°C / short term +120°C
flame resistance:	medium till good
ozone:	good
water:	good
oil and grease:	vegetable limited till good animal limited till good mineral limited till good
fuel:	not resistant

important:

Our technical service is based on experiences, the values are intended only as a source of information and are given without guarantee and do not constitute a warranty. Users should independently determine prior to use the suitability of this material for their purposes.

technical information

solid rubber in NBR (Perbunan)

elastomer: ACRYLONITRIL-BUTADIENE-COPOLYMER (NBR)

special characteristics: homogenous
continuous extruded and vulcanized
no adhesive-connection

colour: black
(according to available request other colours)

density: ca. 1,35 g/cm³

shore: 55 - 65 – 75 ±5

dimensional tolerance: according to DIN ISO 3302-1 E2

resistance

temperature: from –35°C till +90°C

fuel and grease: excellent

aliphatic hydrocarbon: excellent

water: good

important:

Our technical service is based on experiences, the values are intended only as a source of information and are given without guarantee and do not constitute a warranty. Users should independently determine prior to use the suitability of this material for their purposes.

technical information

solid rubber in FPM/FMQ (VITON®)

elastomer:	FLUOR RUBBER (FPM/FMQ)
special characteristics:	continuous extruded and vulcanized
	no adhesive-connection
colour:	black
density:	ca. 1,88 g/cm ³
shore:	60 – 70 - 75 ±5
tensile strength:	≥ 140 kg/cm ²
elongation:	≥ 250 %
resistance to tearing:	≥ 25 kg/cm
compression set:	after 22 hours with 175 °C: ≤ 30% (crushing 25%)
dimensional tolerance:	according to DIN ISO 3302-1 E2

resistance

chemicals:	excellent
hydrochloric-/sulphuric acid (50%):	very good
nitric acid (60%):	very good
hydrocarbon:	very good
oil and lubricant:	very good

age limit in warm air (70 hours to 275 °C):

change of hardness:	+5
change of tensile strength:	-35%
change of breaking strain:	-10%

age limit in fluid ASTM B (7 days at room-temperature):

change of hardness:	+2
change of volume:	+1,5%

age limit in fluid ASTM c (7 days at room-temperature):

change of hardness:	-5
change of volume:	+5%

important:

Our technical service is based on experiences, the values are intended only as a source of information and are given without guarantee and do not constitute a warranty. Users should independently determine prior to use the suitability of this material for their purposes.

VITON® = Entered registered trade mark of the company DuPont

technical informations

solid rubber in NR (Natural Rubber)

elastomer:	NATURAL RUBBER (NR/Para)
special characteristics:	homogenous continuous extruded and vulcanized no adhesive-connection
colour:	grey
density:	ca. 1,11 g/cm ³
shore:	45 ±5
elongation:	550%
tensile strength:	16 MPa
resistance to tearing:	50 kN/m
compression set:	30% max.
dimensional tolerance:	according to DIN ISO 3302-1 E2

resistance

temperature:	air oven (till 60°C) moderate
stiffening in cold:	good
flame resistance:	dissatisfied
ozone and weathering:	dissatisfied
acid:	dissatisfied
alkaline:	moderate
water:	good
ketone:	moderate
oil and grease:	dissatisfied
aromatic hydrocarbon:	dissatisfied
solvent with chlorine:	dissatisfied
fuel:	dissatisfied
dielectric strength:	moderate

important:

Our technical service is based on experiences, the values are intended only as a source of information and are given without guarantee and do not constitute a warranty. Users should independently determine prior to use the suitability of this material for their purposes.

technical information

silicone rubber

elastomer:	METHYLVINYLPOLYSILOXAN (VMQ)
special characteristics:	continuous extruded and vulcanized water - and organic-products refused scentless and no taste physiological clean and bacteriological indifferent repeatedly sterilizable contains no poisonous materials not corrosive – not adhesive
colour:	translucent
density:	ca. 1,20 g/cm ³
hardness:	60° shore A
tensile strength:	90 kg/cm ³
elongation:	420%
resistance to tearing:	18 kg/cm
dimensional tolerance:	according to DIN ISO 3302-1 E3
compressing set:	after 22 hours with 175°C: 34%
resistance	
temperature:	from -70°C till ca. +220°C – special quality till +250/300°C
weathering, age limit, ozone:	excellent
tropical-climate, ultraviolet rays:	excellent
radioactive- and x-rays:	very good
aliphatic motor- and gear oil:	generally good
distilled water:	very good
seawater:	excellent
chemical resistance:	ask for the different cases with specification of chemical substance
vapour resistance:	1,5 – 2 bar short-term
heat conductivity:	0,18 – 0,23 Kcal. x s ⁻¹ °C ⁻¹
specific heat:	0,3 cal. x gr ⁻¹ °C ⁻¹
specific volume resistance:	3 x 10 ¹⁵ - 10 ¹⁶ Ohm/cm
dielectric tangente by 1 MHz:	2,8 – 3
loss tangente by 1 MHz:	1,10 – 2,50 x 10 ⁻³
breakdown strength 2 mm:	16 KV/mm

Physical-mechanical values are depending on the cross-section of the profile. The quality performed the instructions of the American Material Specification AMS 3195.

important:

Our technical service is based on experiences, the values are intended only as a source of information and are given without guarantee and do not constitute a warranty. Users should independently determine prior to use the suitability of this material for their purposes.

technical information

PVC edge protector profiles with embedded steel base strip

material:	<u>basic profile:</u>	soft-PVC	75 ±5 shore
	<u>retentionlips:</u>	elastic-PVC	57 ±5 shore
	<u>steelband:</u>	ST 4	16 x 0,3 mm
	<u>tightreach:</u>	sponge rubber EPDM-quality – according your request other qualities	

special characteristics: continuous extruded
metal tape broken
no adhesive-connection

colour: black, white, silver
(according to available request other colours)

dimensional tolerance: according to DIN 16941
as combination for sponge rubber according to
DIN ISO 3302-1 E3

resistance

temperature: from –35°C till +80°C

ozone, weathering, uv-light: good

oil and grease:	vegetable	inconstant
	animal	inconstant
	mineral	moderate till inconstant

acid, base, ketone, alcohol: moderate till inconstant

important:

Our technical service is based on experiences, the values are intended only as a source of information and are given without guarantee and do not constitute a warranty. Users should independently determine prior to use the suitability of this material for their purposes.

self-adhesive tape for sponge rubber and solid rubber

description

Double coated polyester scrim designed for bonding foamed synthetic rubbers and plastics in the production of gasketing and for cold; it is intended as an assembly aid.

benefits

- Provides excellent initial adhesion to a wide variety of materials.
- Good bonding to uneven surfaces.

surface preparation

It is essential, as with all pressure-sensitive tapes, that the surface to which the tape is applied is clean, dry and free of any grease and oil.

storage and shelf life

6 months when stored at 21°C (70°F), 50% relative humidity, out of direct sunlight.

Product data

Backing	polyester cloth / transparent
Adhesive	synthetic rubber permanent
Liner	kraft paper brown
Total thickness (without liner)	approx.. 0,18mm
Adhesion to steel	≥ 26,0 N/cm
Temp. Resistance	-20°C to +65°C, short term +70°C

important

Information on the above characteristics is based upon tests we believe to be reliable. The values given are typical values that vary according to application conditions. The values are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine prior to use the suitability of this material for their purposes. Any technical modifications are reserved by us.

self-adhesive tape *sk normal* for foam silicone and silicone

description

Double coated polyester scrim designed for bonding foamed synthetic rubbers and plastics in the production of gasketing and for cold; it is intended as an assembly aid.

benefits

- Provides excellent initial adhesion to a wide variety of materials.
- Good bonding to uneven surfaces.

surface preparation

It is essential, as with all pressure-sensitive tapes, that the surface to which the tape is applied is clean, dry and free of any grease and oil.

storage and shelf life

6 months when stored at 20°C (70°F), 50% relative humidity, out of direct sunlight.

Product data

Backing	cotton
Adhesive	pure acrylate
Liner	Polypropylen
Total thickness (without liner)	approx.. 0,08mm
Adhesion to steel	25N/25mm
Temp. Resistance	-30°C to +120°C

important

Information on the above characteristics is based upon tests we believe to be reliable. The values given are typical values that vary according to application conditions. The values are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine prior to use the suitability of this material for their purposes.

Any technical modifications are reserved by us.

self-adhesive tape *sk super* for foam silicon and silicon

description

Double-sided tape, suitable for bonding on siliconized surfaces. The aging resistant polysiloxane adhesive allows a self adhesive equipment of silicone profiles. It is intended as an assembly aid.

Supporting base:	polyester
thickness:	0,023 mm +/-10%
adhesive-type:	mod. Polysiloxan
total thickness:	ca. 0,170 mm +/-15%
Liner:	crepped hard PVC
adhesive-strength – departure of a plate:	≥2 N/cm
Tensile strength:	≥35 N/10mm
Elongation at break:	≥80 %
Flammability:	flame retardant
Insulation class:	B
temperature:	from –40°C till +130°C – short term +175°C

storage and shelf life:

6 months stored cool and dry, at 15-25°C, <65% relative humidity, out of direct sunlight.

important:

Our technical service is based on experiences, the values are intended only as a source of information and are given without guarantee and do not constitute a warranty. Users should independently determine prior to use the suitability of this material for their purposes.

Any technical modifications are reserved by us.

**our factory standard
to lean on the DIN ISO 3302-1
class E 3, E2 and E 1**

This edition invalidates any previous versions.

scale in mm	tolerance group E 3 in mm	tolerance group E 2 in mm	tolerance group E 1 in mm
0 to 1,5	± 0,40	± 0,25	± 0,15
over 1,5 to 2,5	± 0,50	± 0,35	± 0,20
over 2,5 to 4	± 0,70	± 0,40	± 0,25
over 4 to 6,3	± 0,80	± 0,50	± 0,35
over 6,3 to 10	± 1,00	± 0,70	± 0,40
over 10 to 16	± 1,30	± 0,80	± 0,50
over 16 to 25	± 1,60	± 1,00	± 0,70
over 25 to 40	± 2,00	± 1,30	± 0,80
over 40 to 63	± 2,50	± 1,60	± 1,00
over 63 to 100	± 3,20	± 2,00	± 1,30
over 100 to 250	± 4,00	± 2,25	
over 250 to 315	± 5,00	± 2,50	
over 315 to 400	± 6,00	± 3,00	
over 400 to 500	± 7,00	± 3,50	

At one-sided tolerance, therefore only at + or at -, is the declared tolerance quantity doubled, instead of ± 0,50 mm, +1,00 or -1,00 mm.